

# Technical Data Sheet

## PETGCF10 Filament

PETGCF10 is a FFF 3D printing filament, which is produced using a PETG modified material containing 10% carbon fiber. PETGCF10 has excellent dimensional stability and rigidity and is easier to print than PETG filament.

### Features:

Dimensional stability/High strength/Easy-to-print property.

### Properties:

Physical Properties	Test Method	Units	Typical Value
Density	ISO 1183	g/cm <sup>3</sup>	1.27~1.28
Melt Index MFR (220°C/2.16Kg)	ISO 1133	g/10min	10~15
Water Absorption (23°C/24h)	ISO 62	%	< 0.8
Mechanical Properties			
Tensile Strength (X-Y)	ISO 527	Mpa	40~43
Elongation at Break (X-Y)	ISO 527	%	7.5~8.5
Modulus of Elasticity (X-Y)	ISO 527	Mpa	2100~2400
Bending Strength (X-Y)	ISO 178	Mpa	75~85
Izod Impact Strength (X-Y)	ISO 180	KJ/m <sup>2</sup>	3~3.5
Thermal Properties			
HDT@ 0.455 MPa (66 psi)	ISO 75	°C	70
Continuous Service Temperature	IEC 60216	°C	80

## Testing Specimen Printing Conditions:

Test Equipment	Guider IIs (Flashforge)
Nozzle Diameter	0.4mm
Nozzle Temperature	240 °C
Printing Speed	50mm/s
Wall Thickness	1.2mm
Infill	100%
Standard Testing Specimen	Specific dimensions are shown in Attachment 1

**Note:** The above test parameter data are obtained from actual printing, and the printed model has not been annealed.

## Recommended Printing Conditions:

Parameter	
Nozzle Temperature	230~250°C (240°C recommended)
Build Platform Temperature	50~80°C (70°C recommended)
Build Surface Material	Tempered glass, BuildTak, Carbon fiber board
Nozzle Diameter	φ0.4/0.6mm (φ0.4mm recommended)
Nozzle&Gear Material	High-strength steel
Cooling Fan	50~100%
Layer Thickness	0.12~0.3mm
Printing Speed	40~60mm/s (50mm/s recommended)
Travel Speed	60~120mm/s
Ambient Temperature for Printing	Room temperature~65°C
Retraction Length	1~2mm
Retraction Speed	30~50mm/s
Recommended Support Material	Self-supporting

## **Cautions:**

In order to prevent moisture absorption and contamination, supplied packaging should be kept closed and undamaged. For the same reason, partially used filaments should be re-sealed before storage.



Because of the addition of carbon fiber, PETGCF10 filament absorbs moisture more easily than PETG filament, so it should be dried before being used. Using a hot dry air oven at 70°C for at least 5 hours is recommended in order to ensure the success rate and quality of the printed model.

After the printing process, it is recommended to dry the model in an oven at 70°C for 1-3 hours in order to increase the strength of the model.



## **Disclaimer:**

Since the conditions of use and applicable laws may vary from place to place and from time to time, customers are responsible for determining whether the products and product information in this document are suitable for customers to use, and ensuring that their workplaces and methods of handling products comply with applicable laws and other governments regulations. Our company does not assume any responsibility or obligation for the information in this document, nor does it provide any guarantee. All implied warranties regarding the saleability of the product or the applicability for a particular purpose under this document are expressly excluded here.



# Attachment 1: Testing Specimen Size and Printing Direction



Tensile testing specimen; ASTM D638 (ISO 527, GB/T 1040)



Flexural testing specimen; ASTM D790 (ISO 178, GB/T 9341)



Impact testing specimen; ASTM D256 (ISO 179, GB/T 1043)